

Development of radiation- tolerant superconducting magnet for muon sources at J-PARC

M. Yoshida; KEK/J-PARC Cryogenics Section

J-PARC symposium



Oct. 17, 2024

Contents

- Design of radiation-tolerant superconducting magnet
- Irradiation tests on magnet materials
- R&D of HTS magnet for the next generation muon sources

Magnets for High Intensity Muon Sources

- Large aperture and high magnetic field to capture π, μ
 - Radiation from production target
- Long solenoid to decay π , transport μ



SuperOmega


U-line@J-PARC MUSE

$\phi 380$



DOI: [10.1109/TASC.2010.2089405](https://doi.org/10.1109/TASC.2010.2089405)

- 1MW pulsed beam (50kW(5%) on target)
- 400mSr
- $\sim 4 \times 10^8 \mu^+/s, \sim 10^7 \mu^-/s$



Mu2e


$\sim \phi 1600$

MuSIC

DC muon source@RCNP


Cryogen-free magnets

$\phi 900$



- 400W proton beam (100W on target)
- pion capture system
- $\sim 3 \times 10^8 \mu^+/s, \sim 10^8 \mu^-/s$


DOI: [10.1109/TASC.2010.2088360](https://doi.org/10.1109/TASC.2010.2088360)



COMET

under construction
at J-PARC


a Muon collider



L. Bottura, 2024

COMET Pion Capture Solenoid



Goal: $10^{11} \mu^-/\text{sec}$



Radiation Environment for COMET Pion Capture Solenoid

- COMET Phase-2
 - 56kW 8GeV proton beam
 - Tungsten target
 - Tungsten shield
- Peak heat deposit
 - ~ 40 mW/kg
 - 1MGy for 300day operation
- Peak neutron flux
 - $\sim 4 \times 10^{14}$ n/m²/s
 - 10^{21} n/m² for 30day operation

Radiation-tolerant magnet is mandatory



Irradiation Effects in Magnet Materials

- Organic polymer


- Insulator
- GFRP
- Adhesive
- Impregnation

Degradation of
mechanical strength,
electrical insulation

- Pure metal

- Stabilizer
- Thermal conductor

Degradation
of conductivity





Displacement per Atom (DPA) = ⁶ fraction of interacted atoms

Coil Structure

- Aluminum stabilized SC cable
 - for less nuclear heating
- Radiation resistant insulator, resin
 - Polyimide film, Bismaleimide-Triazine resin
 - Boron-free glass in GFRP
- Pure aluminum strips in between layers
 - to cool down a coil inside

DESIGN PARAMETERS OF CAPTURE SOLENOID MAGNET

Item	Value
Conductor	Aluminum stabilized SC cable Al/Cu/NbTi = 7.3/0.9/1
Cable dimensions	15.0 × 4.7 mm ² (without insulation) 15.3 × 5.0 mm ² (with insulation)
Cable insulation	Polyimide film/Boron-free glass cloth/BT-Epoxy prepreg.
Magnet length	~6 meters
Num. of coils	10
Operation current	2700 A
Max. field on conductor	5.5 T (T _{cs} = 6.5 K) ^a
Stored energy	47 MJ
Coil inner diameter	1324 mm (CS0~MS2) 500 mm (TS1a~TS1e) 800 mm (TS1f)




Al stabilized SC cable


- Size: 4.7x15mm
- Offset yield point of Al@4K: >85MPa
- RRR@0T: >500
- Al/Cu/SC: 7.3/0.9/1
- 14 SC strands: 1.15mm dia.

Irradiation test by reactor neutrons


- Kyoto Univ. Research Reactor Institute
- 5MW max. thermal power
- Cryostat close to reactor core
- Sample cool down by He gas loop
 - 10K – 20K
- Fast neutron flux(>0.1MeV)
 - 1.4×10^{15} n/m²/s@1MW thermal power




[2] M. Okada et al., NIM A463 (2001) pp213-219



KUR-TR287 (1987)






Neutron Irradiation / Annealing Effect on Electrical Resistance of Stabilizer



- Al: 0.03 nOhm.m for 10^{20} n/m²
- Cu: 0.01 nOhm.m for 10^{20} n/m²
- All **Al** samples show **“full” recovery** of electrical resistivity after thermal cycle to RT.

Proton irradiation test at J-PARC

- 3GeV-30GeV proton beam from MR
- Installed in 2019



	purity	RRR	shape
Al	>99.99%	580	wire ϕ 0.25mm
Cu	99.995%	306	wire ϕ 0.25mm
W	99.95%	28	wire ϕ 0.25mm

- Pure metal wire cooled by GM cryocooler
- Sample can be inserted to the beam line on demand.
 - remote handling

Proton Irradiation

- Pure aluminum and copper was irradiated by 8GeV and 30GeV protons
- Damage rate is reproduced by simulation with extensive Molecular Dynamics (arc-dpa model)
- **Recovery was observed**
 - Could be perfect even in Cu in this high energy range

TABLE V
DAMAGE RATE BY PROTON IRRADIATION

Material	30 GeV protons	8 GeV protons
Aluminum	1.03±0.12 (~100%)	1.05±0.15
Copper	3.55±0.23 (~100%)	3.88±0.27
Tungsten	95.8±5.6 (26%)	95.3±5.6



Values are in the unit: $10^{-31}\Omega m^3$ with errors indicating statistical fluctuat only. Recovery rate by thermal cycle after 30 GeV proton irradiation is indica in parentheses.

TABLE III
THE DAMAGE RATE BY NEUTRON IRRADIATION IN EACH IRRADIATION PERIOD.

Sample name	2010 NOV	2011 Sep	2011 Nov	2012 Nov	2013 July	2014 Apr
Al-CuMg	2.4					
Al-5N		2.5				
Al-Y1			2.8	2.9		
Al-Y2			2.6	2.7	2.3	2.2
Al-Ni					2.3	2.3
Cu			0.94 (82%)	1.0 (92%)	0.77 (95%)	0.73 (96%)

Values are in the unit: $10^{-31}\Omega m^3$. Recovery rate by thermal cycle after irradiation is indicated by the values in parentheses for the Cu sample.


KUR neutrons ~MeV



“Repetitive Irradiation Tests at Cryogenic Temperature by Neutrons and Protons on Stabilizer Materials of Superconductor,”
M. Yoshida et al., *IEEE Trans. Appl. Supercond.*, 32(6), 7100405 (2022); doi:10.1109/TASC.2022.3178944

Irradiation Test of GFRPs

- BT(bismaleimide triazine)-Epoxy GFRP has excellent performance.



Flexural strength test w/ G10 sample irradiated at 30 MGy.
Delamination of glass sheets is observed.






Fig. 3. Change in flexural property of GFRPs after gamma-ray irradiation: displacement-load curves ((a) V-direction and (b) H-direction) and flexural strength ((c) V-direction and (d) H-direction).

Coil Temperature during Beam Operation (phase-2)

- Peak temperature in coil is estimated assuming irradiation by 56kW beam operation
- Assume damage rate at $0.03 \text{ n}\Omega\text{m}$ for 10^{20} n/m^2
- Temperature will rise as thermal conductivity degrades by irradiation
- Irradiation damage in aluminum can be recovered perfectly by thermal cycling to room temperature.




- Radiation effects in magnet materials are considered in the magnet design.
- Influence of conductivity degradation is serious for LTS coils, while COMET magnet is expected to survive.
- Need R&D for next generation magnet

Superconductor for the Next Generation Magnet

- Cooling of deposit heat by radiation particles is an issue in **LTS** coils
- **High Temperature Superconductor (HTS)** is better candidate for the next generation magnets
 - Larger heat capacity at higher temperature
 - High tolerance for deposit heat
 - Less refrigerator power at higher temperature
 - Capability for higher field

REBCO tape conductor
Re=Gd,Y,Eu,...




Conceptual Design of Capture Solenoid for J-PARC MLF 2nd Target Station (TS2)



(10 years operation)

- ❑ Heat Deposit: **~450 W**
- ❑ Neutron fluence: **~ 10^{22} n/m²**
- ❑ Absorbed Dose: **> 100 MGy**

PHITS Code



AVG. flux at the top 100 mm of the coil



- Stack of double pancake coil
- ID=1600 mm
- Conductor : **REBCO**
- Operation Temperature: **20 K** (He gas cooling with pipe)
- Peak Field: **1.11 T** at center, **2.25 T (B//c)** at coil




Radiation effects on REBCO tape is under investigation

Neutron Irradiation Tests on REBCO conductor



- Neutron irradiation at **JRR3** and **BR2** reactor is performed under the GIMRT program of the IMR, Tohoku Univ.
- PIE with an external field up to 15.5 T at IMR-Oarai.

Variable Temperature Insert

Temperature Range	4 ~ 80 K
Max. Current	500 A
Max. External Field	15.5 T



Results on GdBCO irradiated at BR2



M. Iio, M. Yoshida, T. Nakamoto, T. Ogitsu, M. Sugano, K. Suzuki, and A. Idesaki, "Investigation of Irradiation Effect on REBCO Coated Conductors for Future Radiation-Resistant Magnet Applications," IEEE Trans. Appl. Supercond., vol. 20, no. 6, Sep. 2022, Art. no. 6601905.

Degradation was observed at $8 \times 10^{21} \text{ n/m}^2$

Gd has huge cross section (49kb) of thermal neutrons \rightarrow 9b on Y, 5kb on Eu

\rightarrow PIE on YBCO, EuBCO samples irradiated at JRR3 will be done in this year

Study of Aluminum-stabilized HTS conductor

- Commercial REBCO tape conductor has less stabilizer, a few 10s micro-meter-thick copper
- More stabilizer is necessary to avoid thermal runaway at quench
- Development of Al-stabilized HTS conductor was initiated

- REBCO tape is soldered on both side of copper-clad aluminum (CCA) flat wire
- No degradation by soldering process was found.
- Trial with thicker aluminum is planed

- CCA: **0.17 mm thick, 4 mm wide**
(T_{Cu} =0.015-0.02 mm, Al: 8030 Alloy)
- REBCO: YBCO with AP **x2**
(SCS4050HM, W4mm, **I_c= 70A**)
- Joint length: 200 mm
- Temperature conditions:
195°C-2min / 210°C-2.5min / 220°C-4min

Study of Mineral Insulation

- Insulation is another key issue of radiation tolerance
- Study of mineral insulation is underway
- Spray coating of alumina-silica on REBCO tape
 - heat treatment at 100°C
 - 30 μm -thick ceramic layer withstands 2kV
 - No degradation by coating process was found
- Test coil with mineral insulation is developed and tested with ext. field of 9T at BNL
 - Analysis underway

Summary

- Radiation-tolerant superconducting magnet is necessary for high-intensity muon source
- Radiation effects on magnet materials were investigated so far.
 - The results are adopted in the design of the COMET Pion Capture Solenoid
- R&D for further radiation tolerance is on-going for the next generation magnets
 - Irradiation tests on REBCO tape
 - Studies on mineral-insulated aluminum-stabilized HTS coil